



Hersteller/Manufacturer: German Special Alloys GmbH | Carl-Friedrich-Benz-Str. 1b | 47877 Willich | Germany

C € 0044

Hergestellt für/ Produced for:



Realloy e.K. | Moerserstraße 232 | 47803 Krefeld | Germany | Fon: : +49 (0)2151-4864978 | Fax: +49 (0)2151-4864981 | Mail: info@realloy.net

Instructions for Use metal-ceramic alloy

realloy N+ Powder

15 µm - 45 µm

realloy N+ Powder 15-45 µm is a dental metal-ceramic alloy based on nickel. **realloy N+ Powder 15-45 µm** is free from cadmium, beryllium and lead and fulfils the standards of EN ISO 22674 type 5 for appliances in which parts require the combination of high stiffness and strength, e.g. thin removable partial dentures, parts with thin cross-sections and clasps. **realloy N+ Powder 15-45 µm** can be used as a metal-ceramic alloy.

Composition w_i

Ni	%	62,4
Cr	%	25,0
Mo	%	11,0
Si	%	1,6
Nb, Mn, Fe	%	< 1

Technical data (Standard values, manufactured condition)

Particle size d _i	µm	15-45
Density ρ	g · cm ⁻³	8,2
Vickers hardness	HV 10	200
Linear thermal expansion coefficient α	10 ⁻⁶ · K ⁻¹	13,9
25 - 500 °C		
Linear thermal expansion coefficient α	10 ⁻⁶ · K ⁻¹	14,1
20 - 600 °C		
Highest recommended firing temperature T _{F,max}	°C	980
0,2-% Yield strength R _{p0,2}	MPa	623
Modulus of elasticity E	GPa	183
Elongation at break A ₁₀	%	16,3
Tensile strength (R _m)	MPa	1013

Recommendations for Use

Design

The design is carried out with suitable CAD software in consideration of dental rules. Wall thickness after finishing of the object: at least 0,3 mm. Design the connector as strong and high as possible (height: at least 3,5 mm, width: at least 2,5 mm).

SLM-Process

Avoid dust production while opening the powder container, transportation and filling into the SLM system! Use a suitable SLM system for the particle distribution of **realloy N+ Powder 15-45 µm** and carry out the SLM-Process according to the manufacturer's instructions for the SLM system. Non melted powder can be reused but should be sieved with a powder sieve (80 µm) first. Melted powder cannot be reused by e.g. casting.

Shot Peening

Blast the production platform with spherical ceramic material with Ø 0,125-0,250 mm and 2,5-3,5 bar until a uniform saturation of the surface is visibly achieved.

Stress Relief Heat Treatment

The heat treatment needs to be carried out in a special furnace under argon atmosphere. Place the production platform in an inert gas box with an argon flow of 1-2 L/min and put the box into the cold furnace. Then:

1. Within 60 min heat up to 850 °C and hold the temperature for 60 min.
2. Let the platform cool down. Open furnace door earliest at 600 °C or lower temperature, remove the inert gas box and stop the argon flow.

Firing of Ceramics

Use commercially available dental ceramics for nickel-based metal alloys with a suitable linear thermal expansion coefficient. Please follow the associated work instructions and cooling schemes given by the ceramic manufacturer. After the heat treatment and cooling down:

1. Remove restorations from the plate using a band saw, rotating instruments or pliers. Use pliers to remove the rest of the supports. Carbide cutters are recommended for finishing of the object.
2. Sand blast the surface by use of a pencil-blaster with aluminium oxide 100 µm or 250 µm.
3. Ultrasonically clean the frame in distilled water or degrease with ethyl acetate.
4. The oxide firing is optional, to be done at about 960 °C under vacuum for 5 minutes. Always remove the oxide layer after oxide firing by sand blasting with aluminium oxide and degrease again.
Note: A clean surface is best to avoid bubbles in ceramics.
5. The opaque is applied on the surface by a first thin wash firing and a second evenly covering opaque layer.
Before firing always let the opaque dry for 5-10 minutes at 600 °C.
6. Firing and cooling should be carried out in accordance to the ceramic manufacturer's instructions.
7. After every firing step (dentine bake, build-up and glazing) cooling phase until ca. 750 °C.

Finishing

After firing of the ceramic, polish the frame with suitable grinding and polishing instruments for dental alloys up to high gloss.

Soldering and Welding

Soldering before firing of the frame can be carried out with commercially available solders and high temperature flux. The width of the solder gap should be 0,05-0,2 mm. For welding with a laser use suitable commercially available metal welding wires.

Safety Note

Metal dusts are harmful to health! Avoid dust formation and breathing of dust! Use a dust extractor while handling of powder, finishing and blasting. It is recommended to wear tightly sealed goggles, protective gloves, respiratory protection (FFP3) and dust-resistant protective clothing. Consider allergic hypersensitivities to contents of the alloy. Follow the material safety datasheet. In case of suspected incompatibility with individual elements of this alloy, this should not be used.

Warranty

These application recommendations are based on own experiments and experiences and can therefore only be regarded as guidelines. The dentist or dental technician is responsible for the correct processing of this alloy.



Batch number



Refer to instructions for use



Manufacturer



Not for reuse